12701 S. Ridgeway Ave
Alsip, IL 60803
USA

Toll free: 800-535-3535
+1-708-293-7750
Fax: +1-708-293-7765

Tel: 708-293-7750
info@daubertcromwell.com
www.daubertcromwell.com

Ferro-Pak® 40W

PRODUCT DESCRIPTION

40 lb/ream natural kraft saturated with a nitrite-free formulation for protection of ferrous metals.

TYPICAL PHYSICAL TEST RESULTS	Typical Values	Tappi Test Method
Basis Weight, lbs/ream (3000 sq. ft)	46	T-410
Caliper, mils.	3.9	T-411
Tearing Strength, Elmendorf, gms.		T-414
Machine Direction	81	
Cross Machine Direction	90	
Bursting Strength, psi	40	T-403
Tensile Strength, lbs/inch		T-404
Machine Direction	33	
Cross Direction	14	

These results are typical values and are not to be construed as specifications. If specifications are required, please discuss with your sales representative.

METAL PROTECTION

Aluminum	Not Recommended
Steel, AISI 1010	Protection
Cast Iron	Protection
Brass, Red or White	Not Recommended
Bronze, including Naval	Testing Recommended
Copper	Not Recommended
Cadmium or Cadmium Plated	Not Recommended
Stainless Steel	Protection
Galvanized, hot dipped or electroplated	Not Recommended
Chromium or Chromium Plated	Testing Recommended
Nickel or Nickel Plated	Testing Recommended
Silver or Silver Plated	Not Recommended
Magnesium	Not Recommended
Lead or solder	Not Recommended
Tin or tinplate	Protection
Zinc or White Metal	Not Recommended

"Testing Recommended" indicates product will usually protect this metal type, however, for best results Daubert Cromwell recommends corrosion testing of customer provided samples of metals and all chemicals. "Not recommended" indicates Daubert Cromwell may have other, more effective Daubert Cromwell corrosion inhibitor products. Your sales representative can help recommend the optimal product for specific applications.

SHELF LIFE

36 Months, from date of shipping

This shelf life statement is only valid for product stored in the original shipping container used by Daubert Cromwell and not in high humidity and not at high temperatures. Storage outside these conditions voids this statement.

12/9/2014
Rev. 2/16 sd