Product Data

UNIWRAP® UW35MPI

Corrosion Inhibitor VCI Paper

Description



Uniwrap MPI (UW35MPI) is a 35 lb/ream (57 g/m²) natural kraft saturated with Daubert Cromwell's proprietary multi-metal volatile corrosion inhibitor (VCI) formulation. UW35MPI is designed for general protection of ferrous/non-ferrous metal combinations, including cadmium and zinc galvanized steel, without need for surface-applied oils or rust preventive liquids.

UW35MPI has corrosion inhibitors on both sides and 6-language print on one side to identify it as valuable packaging for metals. Also available with wax coating for molding around small parts, reinforced constructions for extra tear and puncture resistance, and poly coated for moisture resistance.

Features



Proven Daubert Cromwell corrosion inhibitor chemistry

- Metals protected: Mild carbon steel, cast iron, zinc and zinc galvanized, copper, nickel-plated steel, brass and bronze.
- Safe and easy to use; no special handling required
- No heavy metals, chromates, phosphates, or secondary amines
- Replaces oil, grease, and traditional corrosion prevention methods
- Parts remain clean, dry and ready to use immediately
- RoHS compliant
- Fully recyclable and repulpable.
- Compatible with Daubert Cromwell rust preventive liquids, emitters and films.

Typical Applications



For transport, export, storage of :

- Fabricated metal components and assemblies
- Engines and large machinery
- Frames, stampings, doors,
- Bearings, gears, valves, pistons
- Brake parts, automotive parts

To use, wrap or layer clean parts in UW35MPI paper. Place within 12" (200-300mm) of the metal. The corrosion inhibitors form a protective molecular layer on the surface of the metal. When the parts are unwrapped, the protective layer immediately begins to dissipate. Parts are clean, corrosion-free and ready to use. No further processing is necessary prior to use.

Uniwrap® Product Family

Product	Basis Weight	Construction	Description	Protection
UW30MPI	30 lb ream /49 g/m²	Natural kraft	General protection	Multi-metal
UW33MPI	35 lb ream/ 57 g/m²	Wax-coated kraft	Wax-coated kraft	Multi-metal
UW35MPI	*35 lb ream/57 g/m²*	*Natural kraft*	*General protection*	*Multi-metal*
UW40MPI	40 lb ream/65 g/m²	Natural kraft	General protection	Multi-metal
UW60MPI	60 lb ream/98 g/m²	Natural kraft	General protection	Multi-metal
UW200	35 lb ream/57 g/m²	Natural kraft	Nitrite-free	Multi-metal
UW94MPI Woven	40 lb ream/65 g/m²	Poly laminated to woven fabric for strength	Heavy duty, strong, moisture-resistant	Multi-metal
PC50MPI Scrim	50 lb ream/80 g/m²	Poly laminated to tri-directional scrim	High strength, moisture resistant, durable	Multi-metal

DAUBERT CROMWELL
The Leading Name in Corrosion Prevention®

12701 S. Ridgeway Ave | Alsip, IL 60803 USA | (800) 535-3535
Tel +1 (708) 293-7750 | E-mail: info@daubertcromwell.com | www.daubertcromwell.com

Technical Data

UNIWRAP® UW35MPI

Corrosion Inhibitor VCI Paper

Physical Data

Physical Properties		Typical Values		
Property	**Units**	**Typical Value**		**Test Method**
Finished Weight	lb/ream (g/m²)	40 (65)		T-410
Caliper	mil (µm)	3.8 (97)		T-411
Mullen Burst	psi (kPa)	29 (200)		T-403
		Machine Direction	***Cross Direction***	
Elmendorf Tear	g/ply (N/ply)	59 (0.58)	64 (0.63)	T-414
Tensile Strength	lb/in (kN/m)	27 (4.73)	15 (2.62)	T-404

Protection Time	
Inside Dry Storage	24 Months (min)

Metal	Protection
Mild Carbon Steel and Cast Iron	Provides full protection in contact and vapor phases
Aluminum	Passive; Test for compatibility
Zinc and Zinc Galvanized Steel	Provides full protection in contact and vapor phases
Copper	Provides full protection in contact and vapor phases
Brass[1]	Provides full protection in contact and vapor phases
Bronze	Provides full protection in contact and vapor phases
Silver	May protect; Test for compatibility
Category A[2]	Provides full protection in contact and vapor phases
Category B[3]	May protect; Test for compatibility

1. Brass alloys in the "red" area containing up to 20% zinc will act like copper; brass in the "white" area containing over 20% zinc and will act like Category A metals.
2. Category A metals include zinc, cadmium, nickel, cadmium-plated steel, and nickel-plated steel. These are prone to contact corrosion sensitivity with inhibitor chemicals, but will be protected as shown in the vapor phase.
3. Category B metals include lead, antimony, babbitt alloys, solder, magnesium or magnesium alloys.

Storage

Store in a cool, dry place, away from direct sunlight. Do not store outdoors, in high humidity, or at high temperatures.


Shelf Life

24 months from date of shipping, stored in the original, shipping container used by Daubert Cromwell and not in high humidity and not at high temperatures, or stored outside.

Approvals

RoHS, OEM Approved





WARRANTY The data, statements and recommendations in this product specification sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use. All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products. We make no warranty, express or implied, as to the suitability of any of our products for any particular use, and we shall not be subject to liability from any damages resulting from their use in operations not under our direct control. This warranty is exclusive of all other warranties, express or implied, and no representative of ours or any other person is authorized to assume for us any other liability in connection with the sale of our products.

DAUBERT CROMWELL
The Leading Name in Corrosion Prevention®
12701 S. Ridgeway Ave | Alsip, IL 60803 USA | (800) 535-3535
Tel +1 (708) 293-7750 | E-mail: info@daubertcromwell.com | www.daubertcromwell.com

Rev. JUL 2017|SMD